

MILLAR WESTERN FOREST PRODUCTS LTD.

WHITECOURT PULP DIVISION MILLAR WESTERN PULP (MEADOW LAKE) LTD.

Tel: 780.486.8200 Fax: 780.486.8283

Aspen & Softwood APP/BCTMP for Multi-Ply Boards

Typical Characteristics

GRADE		400/70/00	375/75/00	400/73/100	400/80/100
Freeness	(CSF, ml)	400	375	400	400
Slowness	(SR, ml)	32	34	32	32
Brightness	(% ISO)	70	75	73	80
Bulk	(cm ³ /g)	3.30	3.00	2.95	2.90
Tensile	(m)	3100	3800	1450	1550
Debris	(%, 6 cut Pulmac)	0.09	0.08	0.03	0.03
COD	kg/t	7	8	6	6
Furnish		100% SWD	100% SWD	100% Aspen	100% Aspen

Supplied to customers as a replacement for hardwood and softwood Kraft pulps in a wide range of multi-ply boards. These grades are used to supply bulk and stiffness in the inner plies of multi-ply boards. 85 Brightness Aspen Printing & Writing Grades are used in the top plies of coated boards.

Rev: 2002/06/14

Street Address:
16640 - 111 Avenue, Edmonton, Alberta
Canada T5M 2S5

Mailing Address:
Bag Service 2200, Edmonton, Alberta
Canada T5J 4W2