

MILLAR WESTERN FOREST PRODUCTS LTD.

WHITECOURT PULP DIVISION MILLAR WESTERN PULP (MEADOW LAKE) LTD.

Tel: 780.486.8200 Fax: 780.486.8283

Aspen APP/BCTMP for High Tensile

Typical Characteristics

GRADE		325/85/100 HT	400/85/100 HT	450/85/100 HT
Freeness	(CSF, ml)	325	400	450
Slowness	(SR, ml)	38	32	28
Brightness	(% ISO)	85	85	85
Opacity	(%)	73	71	71
Bulk	(cm ³ /g)	1.80	1.75	1.75
Tensile	(m)	4600	5000	5000
Debris	(%, 4 cut Pulmac)	0.150	0.200	0.250
COD		12	12	12
Furnish		100% Aspen	100% Aspen	100% Aspen

Supplied to customers primarily as a replacement for hardwood Kraft pulps in a wide range of printing & writing papers and specialties such as release papers, carbonless etc.

Rev: 2002/06/14

Street Address:
16640 - 111 Avenue, Edmonton, Alberta
Canada T5M 2S5

Mailing Address:
Bag Service 2200, Edmonton, Alberta
Canada T5J 4W2